

For almost 100 years, SGI has been a leader in supplying specialized mineral products to the North American building materials industry. Consistent, high-quality products, science-backed solutions, and exceptional customer service set SGI apart, and make SGI products the preferred choice.

Granule Properties	Typical
Specific Gravity (SGI HLP-74)	2.60-2.82
Bulk Density - Loose in lbs./ft <sup>3</sup> (SGI MP-13)	87-95
Baserock Hardness - Barrett (SGI MP-7)	>80
Moisture	<0.2%

## Granule Screen Grading (SGI MP-5 or MP-81)

STANDARD SIEVE		PERCENT RETAINED	
Tyler	U.S.	Minimum	Maximum
8	8	0	Trace
10	12	4	10
14	16	30	45
20	20	25	35
28	30	14	24
35	40	2	9
Pan	Pan	0	2

## Color

Available in shades of black, gray, white, buff, brown, tan, red, blue, and green.

Fired granule appearance prior to oiling will be +/-1.0 color units of standard L, a, b scales (SGI MP-23).

Color Permanence is demonstrated by long-term performance in natural weathering and short-term testing using accelerated weathering equipment.

## Availability

SGI | Annapolis Plant Annapolis, MO Plant Phone: 573-598-4235 Customer Service: 866-266-8503